



**NSF/ANSI 44-61 CERTIFIED FOR  
MATERIAL SAFETY**

**RESINTECH CGS** is a sodium form standard crosslinked gel strong acid cation resin. **CGS** is optimized for residential applications that require good regeneration efficiency and high capacity. **RESINTECH CGS** is intended for use in all residential and commercial softening applications that do not have significant amounts of chlorine in the feedwater. **CGS** is supplied in the sodium form.

## FEATURES & BENEFITS

- RESIDENTIAL SOFTENING APPLICATIONS**

Resin parameters are optimized for residential softeners

- LOW COLOR THROW**

- SUPERIOR PHYSICAL STABILITY**


93% plus sphericity and high crush strengths together with carefully controlled particle distribution provides long life and low pressure drop

- COMPLIES WITH US FDA REGULATIONS**

Conforms to paragraph 21CFR173.25 of the Food Additives Regulations of the US FDA


Prior to first use for potable water, resin should be backwashed for a minimum of 20 minutes, followed by 10 bed volumes of downflow rinse.

## HYDRAULIC PROPERTIES



### PRESSURE LOSS

The graph above shows the expected pressure loss of *ResinTech CGS* per foot of bed depth as a function of flow rate at various temperatures.



### BACKWASH

The graph above shows the expansion characteristics of *ResinTech CGS* as a function of flow rate at various temperatures.

## PHYSICAL PROPERTIES

Polymer Structure	Styrene/DVB
Polymer Type	Gel
Functional Group	Sulfonic Acid
Physical Form	Spherical beads
Ionic Form as shipped	Sodium
Total Capacity Sodium form	>1.8 meq/mL
Water Retention Sodium form	40 to 52 percent
Approximate Shipping Weight Sodium form	50 lbs./cu.ft.
Screen Size Distribution (U.S. mesh)	16 to 50
Maximum Fines Content (<50 mesh)	1 percent
Minimum Sphericity	90 percent
Uniformity Coefficient	1.6 approx.
Resin Color	Amber

Note: Physical properties can be certified on a per lot basis, available upon request

## SUGGESTED OPERATING CONDITIONS

Maximum continuous temperature Sodium form	250°F
Minimum bed depth	24 inches
Backwash expansion	25 to 50 percent
Maximum pressure loss	25 psi
Operating pH range	0 to 14 SU
Regenerant Concentration Salt cycle	10 to 15 percent NaCl
Regenerant level	4 to 15 lbs./cu.ft.
Regenerant flow rate.	0.5 to 1.5 gpm/cu.ft.
Regenerant contact time	>20 minutes
Displacement flow rate	Same as dilution water
Displacement volume	10 to 15 gallons/cu.ft.
Rinse flow rate	Same as service flow
Rinse volume	35 to 60 gallons/cu.ft.
Service flow rate	1 to 10 gpm/cu.ft.


Note: These guidelines describe average low risk operating conditions. They are not intended to be absolute minimums or maximums.

For operation outside these guidelines, contact ResinTech Technical Support


## APPLICATIONS

### SOFTENING

RESINTECH CGS is a standard crosslinked cation resin optimized for residential and commercial applications. This type of resin is easier to regenerate than the higher crosslinked resins. CGS has marginal resistance to chlorine and other oxidants and is not ideal for high temperature and other high stress applications.



Capacity and leakage data are based on the following: 2:1 Ca:Mg ratio, 500 ppm TDS as CaCO<sub>3</sub>, 0.2% hardness in the salt and 10% brine concentration applied co-currently through the resin over 30 minutes. No engineering downgrade has been applied.



East Coast - West Berlin, NJ p:856.768.9600 • Midwest - Chicago, IL p:708.777.1167 • West Coast - Los Angeles, CA p:323.262.1600

**CAUTION: DO NOT MIX ION EXCHANGE RESIN WITH STRONG OXIDIZING AGENTS.** Nitric acid and other strong oxidizing agents can cause explosive reactions when mixed with organic materials, such as ion exchange resins. MATERIAL SAFETY DATA SHEETS (MSDS) are available for all ResinTech Inc. products. To obtain a copy, contact your local ResinTech sales representative or our corporate headquarters. They contain important health and safety information. That information may be needed to protect your employees and customers from any known health and safety hazards associated with our products. We recommend that you secure and study the pertinent MSDS for our products and any other products being used. These suggestions and data are based on information we believe to be reliable. They are offered in good faith. However we do not make any guarantee or warranty. We caution against using these products in an unsafe manner or in violation of any patents; further we assume no liability for the consequences of any such actions.

RESINTECH is a registered trademark © of RESINTECH INC.

CGS rev 1.1